


DATA SHEET

WALL & CEILING ACRYLIC



- EXCELLENT WHITENESS
- HIGH OBLITERATION
- DURABLE MATT FINISH

SECTION A: DESCRIPTION

A good quality general purpose water-based matt acrylic paint for interior and exterior surfaces with excellent opacity, available in white and a range of colour card colours. Matt finish to hide imperfections and is non-yellowing. Formulated to meet the specification of S.A.B.S. 1586:2007 Grade 2.

SECTION B: COMPOSITION

Co-polymer emulsion

SECTION C: PHYSICAL PROPERTIES

Colour:	White and as per colour card
Appearance:	Matt
Gloss:	<10% @ 85°
Viscosity:	95 - 100 Ku @ 25°C
S.G.:	1.25 - 1.51 (depending on colour)
Mass Solids:	57 - 62%
Volume Solids:	37 - 42%
Shelf Life:	12 Months
Storage Conditions:	Normal
Pack Size:	1l, 5l, 10l, 20l

SECTION D: APPLICATION PROPERTIES

Method:	Brush, airless spray or roller
Spreading Rate:	7 - 9m ² /l
Number of coats:	Two
Drying Time @ 250 C:	Hard 4hrs (depending on moisture and humidity). Allow 14 days to cure before washing.
Overcoating Time @ 250 C:	4 hrs
Thinning:	Not Applicable
Cleaning Solvent:	Water
Recommended systems:	As described above
Recommended DFT:	50 microns

SECTION E: PRECAUTION

Flash point:	Water-based
Toxicity:	See M.S.D.S.

SECTION F: SURFACE PREPARATION

- All surfaces must be thoroughly clean, dry, free from grease, dirt or old flaking paint.
- All loosely adhering material and powder, i.e. Distemper or Lime, must be removed and a coat of Excelsior SURFCON (Surface Conditioner) be applied and allow ±18 hours to dry.

NEW WOODWORK

- Rub down with fine sandpaper and seal knots.
- Prime with Excelsior WOOD PRIMER.
- Follow with one coat Qolor UNIVERSAL UNDERCOAT.

NEW METAL SURFACES

- Metal surfaces must be primed with the appropriate primer!

A. NEW GALVANISED IRON

- Remove storage oil with Excelsior GALVANISED IRON CLEANER and prime with one coat of Excelsior AQUA-METALPRIME ANTI-CORROSIVE PRIMER.



DATA SHEET

WALL & CEILING ACRYLIC

6
YEAR+
LIFE EXPECTANCY

Qolor
switched on Coatings!

- EXCELLENT WHITENESS
- HIGH OBLITERATION
- DURABLE MATT FINISH

B. NEW MILD STEEL

- Prime with H2O PRIMER RED OXIDE etching water-based primer. (New formulation) or AQUA METALPRIME ANTI-CORROSIVE PRIMER.
or Alkyd based GP RED OXIDE PRIMER
or Excelsior ZP PRIMER (with anti-corrosive Zincphosphate pigments).

NEW PLASTER

Once plaster is completely dry. Apply one coat of:

- Qolor PLASTER PRIMER (Water-based).

PREVIOUSLY PAINTED EMULSION (PVA/Acrylic) SURFACES

- Remove dirt and grime with SUGAR SOAP.
- Loose material must be removed with sandpaper.
- Seal powdery surfaces with Excelsior SURFCON (Surface Conditioner).

PREVIOUSLY PAINTED ENAMEL (Hi-gloss or Eggshell) SURFACES

- Sandpaper thoroughly.
- Apply one coat of Qolor UNIVERSAL UNDERCOAT and allow ± 18 hours to dry.

IMPORTANT!

- Stir well before use.
- Allow 7 days to cure before washing.
- Do not paint if rain is imminent or in damp conditions.

SAFETY INFORMATION

- Keep out of reach of children.
- Ensure adequate ventilation during use.
- Do not smoke or eat while painting.
- Avoid contact with eyes and skin: rinse with water and consult a doctor.
- If ingested seek medical attention immediately and do not induce vomiting.
- Store container in a cool and dry area.

SECTION G: NOTE

No guarantees are implied by the recommendations contained herein; since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.

